



Clear Grip 105g/m² (75µm)

	TESTS	NORM	UNIT	SM/ST	MAIN VALUE	DEVIATION
TEXTURE	Weight	NFT 54-101	g/m ²		135,1	1,4
	Thickness		µm		218,6	4,1
	Density (23°C)	ASTM D. 1505	g/cm ³		1,395	
MECHANICAL PROPERTIES	Breaking strength in traction	ASTM D.882	daN/mm ²		18	
	Elongation		%		140	
AIR/WATER POROSITY	Cobb 60s.	T441-OM98	g/m ²	recto	10	
			g/m ²	verso	10	
FRICITION	Static friction coefficient	ISO 8295		SM	0,99	0,09
	Sliding angle		°	SM	44,7	
HEALTH	Toxicity				none	
	Skin irritation				none	
	Food contact aptitude	Reg. N°CE 1935/2004			Exemption of food contact aptitude in normal conditions of use	
ENVIRONMENT	Reuse	NF 13429			yes	
	Content of recycled	measured	%		0	