



GRIP SHEET

GS1-60



FRICTION

Sliding angle 42° (NF Q03-083, 1993 *)

** Measurement has been hold in conditions of the norm NF Q03-083, non slide side versus recycled paperboard. The friction coefficient is given as an indication. Friction properties are dependent of the surface, the weight of the product and its dimensions. Before validating the product, a test in real conditions of use is required.*

TESTS	NORMS	VALUES	DEVIATION
Weight	ISO 536	90 g/m ²	± 5%
Thickness	ISO 534	84.5 µm	± 5%
Breaking strength in traction	ISO 1924-2	SM 5.2 kN/m	± 0.2 kN/m
		ST 2.7 kN/m	
Bursting strength	ISO 2758	245 kPa	± 30 kPa

ENVIRONMENT

- Energetically valuable
- Reusable

HEALTH

- No toxicity
- No skin irritation

REGULATORY

- Compliant to Directive 94/62/CE
- Compliant to REACH Regulation
- Food compliant (for dry and moist direct contact)