



GRIP SHEET 240 photo



FRICTION

Sliding angle 44° (NF Q03-083, 1993 *)

According to the friction properties required, the antiskid coating can be declined in various models. The antiskid efficiency stay the same, but only focused on the coated areas.

| TESTS | NORMS | 100% | Light coating | Square | DEVIATION |
|-------------------------------|------------|----------------------|----------------------|----------------------|------------|
| Weight | ISO 536 | 270 g/m ² | 260 g/m ² | 252 g/m ² | ± 20% |
| Thickness | ISO 534 | 339 µm | | | ± 20% |
| Breaking strength in traction | ISO 1924-2 | SM | 11.6 kN/m | | ± 0.3 kN/m |
| | | ST | 7.3 kN/m | | |
| Bursting strength | ISO 2758 | 508 kPa | | | ± 37 kPa |
| Dimensions | | According to order | | | ± 2% |

** Measurement has been hold in conditions of the norm NF Q03-083, non slide side versus recycled paperboard. The friction coefficient is given as an indication. Friction properties are dependent of the surface, the weight of the product and its dimensions. Before validating the product, a test in real conditions of use is required.*

REGULATORY

- Compliant to Directive 94/62/CE
- Compliant to REACH Regulation
- Usable in food process, indirect contact

ENVIRONMENT

- Entirely recyclable
- Reusable



HEALTH

- No toxicity
- No skin irritation