



CLEAR GRIP

105g/m²(75µm)

FRICTION

Sliding angle 44,7° (NF Q03-083, 1993 *)

TESTS	NORMS	100%	DEVIATION
Film weight	NFT 54-101	105 g/m ²	± 2 %
Thickness		218,6 µm	± 2 %
Density (23°C)	ASTM D.1505	1,395 g/cm ³	± 2 %
Breaking strength in traction	ASTM D. 882	180 N/mm ²	± 2 %
Elongation		140 %	± 2%
Cobb 60s.	T441-OM98	10 g/m ²	± 2 %
Static friction coefficient	ISO 8295	0,99	± 2 %

** Measurement has been hold in conditions of the norm NF Q03-083, non slide side versus recycled paperboard. The friction coefficient is given as an indication. Friction properties are dependent of the surface, the weight of the product and its dimensions. Before validating the product, a test in real conditions of use is required.*

REGULATORY

- Compliant to Directive 94/62/CE
- Compliant to REACH Regulation

ENVIRONMENT

- Reusable

HEALTH

- No toxicity
- No skin irritation

