



# GRIP SHEET 150 photo



## FRICTION

Sliding angle 44° (NF Q03-083, 1993 \*)

According to the friction properties required, the antiskid coating can be declined in various models. The antiskid efficiency stay the same, but only focused on the coated areas.

## DIMENSIONAL TOLERANCES :

Length and Width : ± 2%

TESTS	NORMS	100%	Alternate stripes	Light coating	Square	DEVIATION
Paper weight	ISO 536	150 g/m <sup>2</sup>				± 20%
Thickness	ISO 534	286 µm				± 20%
Breaking strength in traction	ISO 1924-2	SM	9 kN/m			± 0.4 kN/m
		ST	6.1 kN/m			
Bursting strength	ISO 2758	469 kPa				± 15 kPa

\* Measurement has been hold in conditions of the norm NF Q03-083, non slide side versus recycled paperboard. The friction coefficient is given as an indication. Friction properties are dependent of the surface, the weight of the product and its dimensions. Before validating the product, a test in real conditions of use is required.

## REGULATORY

- Compliant to Directive 94/62/CE
- Compliant to REACH Regulation
- Usable in food process, indirect contact

## ENVIRONMENT

- Recyclable on specific equipment
- Reusable



## HEALTH

- No toxicity
- No skin irritation