



105g/m² (50µm)

FRICTION

Sliding angle 44° (NF Q03-083, 1993 *)

According to the friction properties required, the antiskid coating can be declined in various models. The antiskid efficiency stay the same, but only focused on the coated areas.

TESTS	NORMS	100%	DEVIATION
Paper weight	ISO 536	105 g/m ²	± 2%
Thickness	ISO 534	219 µm	± 2%
Breaking strength in traction	ASTM D.882	180 N/mm ²	± 0,4 kN/m
Elongation at break		140%	NA

- * Measurement has been hold in conditions of the norm NF Q03-083, non slide side versus recycled paperboard. The friction coefficient is given as an indication. Friction properties are dependent of the surface, the weight of the product and its dimensions. Before validating the product, a test in real conditions of use is required.
- Quantity tolerance per pallet : ±2%
- Tolerance in length and width of sheet : ±2%

REGULATORY

- Packaging Directive compliant
- REACH compliant

ENVIRONMENT

- Reusable product

HEALTH

- Non-toxic
- Non-irritating